

IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Currently Amended): A method of purifying lithium sulfide ~~wherein lithium sulfide obtained by reacting lithium hydroxide with hydrogen sulfide in an aprotic organic solvent is washed~~, comprising reacting lithium hydroxide with hydrogen sulfide in an aprotic organic solvent to produce lithium sulfide, and washing the lithium sulfide with an organic solvent at a temperature of 100°C or higher wherein the organic solvent used for washing is N-methyl-2-pyrrolidone (NMP) and wherein ~~[[a]] lithium N-methylaminobutyrate (LMAB) content in the~~ washed lithium sulfide is present at a range of 0.1 % by weight or less.

Claim 2 (Canceled).

Claim 3 (Canceled).

Claim 4 (Currently Amended): A lithium sulfide obtained by the method according to Claim 1, wherein a total content of sulfur oxides in the washed lithium sulfide is 0.15 % by weight or less ~~and wherein a lithium N-methylaminobutyrate (LMAB) content is 0.1 % by weight or less.~~

Claim 5 (Previously Presented): A solid electrolyte for a lithium rechargeable battery comprising the lithium sulfide according to claim 4.

Claim 6 (Original): The solid electrolyte for a lithium rechargeable battery according to claim 5, wherein the ionic conductance is  $1 \times 10^{-3}$  S/cm or higher.

Claim 7 (Previously Presented): A solid battery comprising the solid electrolyte for a lithium rechargeable battery according to claim 5.

Claim 8 (Previously Presented): A solid battery comprising the solid electrolyte for a lithium rechargeable battery according to claim 6.

Claim 9 (Previously Presented): The method according to Claim 1, comprising:  
reacting lithium hydroxide with hydrogen sulfide at a temperature of 0 to 150 °C in an aprotic organic solvent to obtain a lithium sulfide;  
removing the aprotic organic solvent by decantation at a temperature of 100 °C or higher under an inert gas to provide a solid lithium sulfide;  
adding an fresh aprotic organic solvent to the solid lithium sulfide to provide a dispersion of lithium sulfide;  
stirring the dispersion of lithium sulfide at a temperature of 100 °C or higher; and  
drying the stirred dispersion of lithium sulfide under a stream of inert gas at a normal pressure.

Claim 10 (Canceled).

Claim 11 (Currently Amended): The lithium sulfide according to Claim [[1]]4, wherein ~~the~~ lithium N-methylaminobutyrate (LMAB) ~~content~~ in the washed lithium sulfide is present at a range of 0.0005 % by weight or less.

Claim 12 (Currently Amended): The lithium sulfide according to Claim [[1]]4, wherein a total sulfur oxide content in the washed lithium sulfide is 0.001 % by weight or less.

Claim 13 (Currently Amended): The lithium sulfide according to Claim [[1]]4, wherein the total sulfur oxide content in the washed lithium sulfide is 0.001 % by weight or less and [[the]] lithium N-methylaminobutyrate (LMAB) ~~content~~ in the washed lithium sulfide is present at a range of 0.0005 % by weight or less.

Claim 14 (Previously Presented): The method according to Claim 1, wherein the aprotic organic solvent in said reacting is identical to the aprotic organic solvent for washing.

Claim 15 (Previously Presented): The method according to Claim 1, wherein the temperature of the organic solvent used is lower than the boiling temperature of the organic solvent.

Claim 16 (Currently Amended): The method according to Claim 1, wherein the aprotic organic solvent in said reacting is selected from the group consisting of N,N-dimethylformamide, N,N-diethylformamide, N,N-dimethylacetamide, N,N-dipropylacetamide, and N,N-dimethyl benzoic acid amide, N-methylcaprolactam, N-ethylcaprolactam, N-isopropylcaprolactam, N-isobutylcaprolactam, N-n-propylcaprolactam, N-n-butylcaprolactam, and N-cyclohexylcaprolactam; N-methyl-2-pyrrolidone (NMP), N-ethyl-2-pyrrolidone, N-isopropyl-2-pyrrolidone, N-isobutyl-2-pyrrolidone, N-n-propyl-2-pyrrolidone, N-n-butyl-2-pyrrolidone, N-cyclohexyl-2-pyrrolidone, N-methyl-3-methyl-2-pyrrolidone, N-ethyl-3-methyl-2-pyrrolidone, N-methyl-3,4,5-trimethyl-2-pyrrolidone, N-

methyl-2-piperidone, N-ethyl-2-piperidone, N-isopropyl-2-piperidone, N-methyl-6-methyl-2-piperidone, and N-methyl-3-ethyl-2-piperidone, or a mixture thereof.

Claim 17 (Canceled).

Claim 18 (Currently Amended): ~~[[A]]~~The lithium sulfide obtained by the method according to Claim 9, wherein a total content of sulfur oxides in the washed lithium sulfide is 0.15 % by weight or less.